

WiseFlex+ Recyclable Desiccant Film Product Specification Sheet

Product No. MPB602519

Product Structure: OPP19/CPP Metallized25/Des60um

Product Specification:

Appearance		No perforation, foreign matter, odor, adhesion, a
		separation between composite layers, and obvious
		bubbles, wrinkles, dirt, and other defects.
Thickness (um\mil)		105±10\ 4.134±0.394
Grammage (g/m² \ oz/yd²)		120.0±12.0\3.540±0.354
Length (m \ ft)		1000.0±25.0\ 3280±82
Width (mm\in)		50.0 ~ 500.0±1.0\ 1.969 ~ 19.685±0.039 501 ~ 990±2.0\19.724 ~ 38.976±0.079
Diameter	Core Diameter (mm\in)	76.3\3.004
	Estimated roll Diameter (mm\in)	≤400.0\15.748
Joints/roll		≤1
Moisture Adsorption Capacity (25°C, RH40%)(g/m² \ oz/yd²)		≥4.0\0.12
Heat seal Strength (N/15mm\ lb./in)		≥12\4.50
Peel Strength (N/15mm\ lb./in)		≥6\2.25
Water Vapor Transmission Rate (38℃, RH90%) (g/(m².24h))		≤0.50
Oxygen Transmission Rate (23°C±2°C) (cm³/(m².24h.0.1Mpa))		≤50
Total Residual Solvent (mg/m²)		≤5.0
Benzene Residue (Test Limit <0.01mg/ m²)		None Detected
Heavy metal (Pb Base) (ppm)		≤1
TAMC (cfu/100cm²)		≤1000
TYMC (cfu/100cm²)		≤100
E. COLI (cfu/100cm²)		None Detected

Packaging Requirement:

1 roll / Aluminum bag (with one Molecular sieve desiccant)/ Bubble wrap/Carton

Packaging label Contains:

PO No., Product Name, Product No., Roll Length, Roll Width, Weight, Batch No., Expiry Date (DD-MM-YYYY)

2024-11-07

Disclaimer

All the above information is based on the known information of the manufacturer and the test and test results. The dealer or user can decide the value of its performance index and the use of the product according to their own requirements. The applications, uses, operations, etc. are not specified, and users are responsible for their own uses and operations.

